

# **POLYHARD**

#### **PRODUCT DESCRIPTION**

The Concrete Protector's Poly Hard is a 3 part urethane polymer product with self leveling qualities.

STANDARD COLORS: Grey
OTHER COLORS ALSO AVAILABLE: Dark Grey, Charcoal, Red, Blue, Green

REVISION DATE: November 9, 2021

### **CURE SCHEDULE (75°)**

**POT LIFE (1.5 GAL VOLUME):** 10-20 minutes

TACK FREE (DRY TO TOUCH): 5-8 hours

RECOAT OR TOPCOAT: N/A
LIGHT FOOT TRAFFIC: N/A

FULL CURE: 28 days

# **COVERAGE**

Recommended for cage wash areas, bottling areas, warehouses, mechanical rooms, restaurants, food processing areas, chemical processing, bakeries.

COVERAGE PER KIT.: 60 sq.ft/kit @ 1/8" thick

30 sq.ft/kit @ ¼" thick

MIX RATIO: 1 Part A + 1 Part B + 1 Part C

**RECOMMENDED FILM THICKNESS:** 1/4 to 1/8"

**PACKAGING INFORMATION:** Kit of Part A (resin) Part B

(hardener) Part C (aggregate)

### PHYSICAL PROPERTIES

FLEXURAL STRENGTH: ASTM C-580=3800 psi COMPRESSIVE STRENGTH: ASTM C-579=6500 psi TENSILE STRENGTH: ASTM C-307=1000 psi ADHESION: ASTM D-7234=>400 psi, Concrete Failure

VISCOSITY: N/A

**ABRASION RESISTANCE:** ASTM D-4060=80 mg loss

ULTIMATE ELONGATION: N/A
HARDNESS: ASTM D-2240=80D
VOLATILE ORGANIC CONTENT: < 5g/l
SHELF LIFE: 6 months in unopened containers

# **CHEMICAL RESISTANCE**

N/A

#### **LIMITATIONS**

Not not apply in temperatures over 100 degrees °F

#### **BENEFITS**

- High tolerance to moisture vapor.
- Superior impact resistance
- Meets USDA, FDA, and CFIA Standards
- Meets California VOC and SCAQMD
- Cold Temps Application



# **POLYHARD**

#### **INSTRUCTIONS**

- 1) Mix Part A and Part B together use a high speed drill (800 RPM) with a 5" Jiffy type-blade for at least 30 seconds.
- 2) Gradually add Part C and mix continuously for at least 2 minutes until a homogenous mix is attained.
- 3) Apply using a ½" notched squeegee and back roll with a loop roller

## NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY:

The Concrete Protector (Division of Incredible Products, LLC), warrants that all products are assembled under rigorous quality assurance specifications and that all information supplied is exact. All information supplied is not to be taken as a warranty, but for you to conduct your own test to determine if the given product is suitable for your distinct purpose. The following list of properties should not be interpreted as specifications. CONVEYED OR SUGGESTED, NO WARRANTY IS BUILT UPON ANY DISCOVERED RESULTS OR INFORMATION YOU WILL DETAIL DURING USE. CONVEYED OR SUGGESTED NO WARRANTY IS BUILT THAT THE GIVEN PRODUCT SHALL BE MARKETABLE OR THAT THE GIVEN PRODUCT WILL BE IT FOR ANY DISTINCT PURPOSE. NO WARRANT IS BUILT UPON SAID INFORMATION OR THAT THE GIVEN PRODUCT WILL NOT INFRINGE UPON ANY PATENT. The Concrete Protector is NOT liable for, direct or indirect, inadvertent or consequential damages. The Concrete Protector's liability is and will only be limited to the net selling price of our products or, at our discretion, the replacement of our products. Upon delivery of our products, your acceptance means that you accept all terms of this warranty even if other documents and or purchase orders astray from the terms of this warranty. No representative, on our behalf, is permitted to make any representation, warranty, or assume liability with any sale of our products. OUR PRODUCTS CONTAIN CHEMICALS THAT CAN CAUSE SERIOUS PHYSICAL INJURY, BEFORE THE USE OF OUR PRODUCTS, READ ALL MATERIAL AND FOLLOW ALL LISTED PRECAUTIONS TO AVOID ANY BODILY HARM